# CanusaTube™ PLA

# Tubular sleeve for pipeline corrosion protection

The CanusaTube™ PLA is a heat shrinkable tubular sleeve designed for corrosion protection of buried and exposed steel pipelines. CanusaTube™ PLA consists of a crosslinked polyolefin backing, coated with a protective heat sensitive adhesive which effectively bonds to steel substrates and common pipeline coatings including polyethylene and fusion bonded epoxy.

### **Rapid & Reliable Installation**

- CanusaTube<sup>™</sup> PLA consists of a unique tubular configuration that has been factory constructed, resulting in a quick and reliable field installation.
- CanusaTube<sup>™</sup> PLA is manufactured with a specially formulated adhesive to accommodate demanding operating temperatures and soil stress conditions.

### **Long Term Corrosion Protection**

- CanusaTube<sup>™</sup> PLA provides excellent resistance to cathodic disbondment resulting in effective long term corrosion protection.
- The high performance crosslinked backing in combination with the specially formulated adhesive is engineered to have excellent resistance against temperature cycling, and chemical and environmental attack.

### **Saves Time & Money**

- With CanusaTube™ PLA's unique construction, less time is required handling, positioning and installing separate closures.
- This feature allows for a fast, simple and complete installation of the sleeve, with no primers required. This minimizes installation time and labour costs while promoting high production rates.





### **Applications**



Oil & Gas



**Water Pipelines** 



**Utility Poles** 



## CanusaTube™ PLA

### Tubular sleeve for pipeline corrosion protection

Sleeve Operating Characteristics	Test Method	Typical Values
Pipeline Operating Temp.		Up to 55°C (131°F)*
Minimum Installation Temp.		60°C (140°F)
Mainline Coating Compatibility		PE, FBE
Adhesive Properties		
Softening Point	ASTM E28	72°C
Lap Shear @ 23°C	ISO 21809-3	60 N/cm²
Backing Properties		
Tensile Strength	ASTM D638	20 MPa
Elongation	ASTM D638	600%
Hardness	ASTM D2240	46 Shore D
Volume Resistivity	ASTM D257	10 <sup>17</sup> ohm-cm
Sleeve Properties		
Adhesion Strength @ 23°C	ISO 21809-3	35 N/cm
Impact Resistance	ISO 21809-3	Pass
Indentation Resistance	ISO 21809-3	Pass
Cathodic Disbondment @ 23°C, 28 days	ISO 21809-3	13 mm rad
Low Temp. Flexibility	ASTM D2671-C	-32°C
Thickness		
Backing (nominal thickness as supplied)		0.6 mm (0.025")
Adhesive (nominal thickness as supplied)		0.9 mm (0.035")

<sup>\*</sup> Actual temperature rating is dependant on specific project requirements and conditions. Please consult your local Canusa representative.

Since 1967, Canusa-CPS has been a leading developer and manufacturer of specialty pipeline coatings for the sealing and corrosion protection of pipeline joints and other substrates. Canusa-CPS high performance products are manufactured to the highest quality standards and are available in a number of configurations to accommodate many specific project applications.

The product information shown here is intended as a guide for standard products.

Consult your Canusa representative for specific projects or unique applications.



### Canusa-CPS A division of ShawCor Ltd.

#### **Head Office**

25 Bethridge Rd. Toronto, ON M9W 1M7 Canada

Tel: +1 416 743 7111 Fax: +1 416 743 5927

#### Canada

Suite 3200, 450 - 1st Street S.W. Calgary, AB T2P 5H1 Canada

Tel: +1 403 218 8207 Fax: +1 403 264 3649

#### **Americas**

2408 Timberloch Place, Building C-8 The Woodlands, TX 77380 USA

Tel: +1 281 367 8866 Fax: +1 281 367 4304

### **Europe & Middle East**

Unit 3, Sterling Park, Gatwick Road, Crawley, West Sussex RH10 9QT United Kingdom

Tel: +44 1293 541254 Fax: +44 1293 541777

#### Asia-Pacific

101 Thomson Road, #11-03 United Square 307591 Singapore

Tel: +65 6749 8918 Fax: +65 6749 8919

### Canusa-CPS is registered to ISO 9001:2008

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the product data sheet when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this data sheet is to be used as a guide and is subject to change without notice. This data sheet supersedes all previous data sheets on this product. E&OE

PDS\_CanusaTube PLA\_rev014



