# Wrapid Coat™ PVC

## **Superior Mechanical Protection**

Wrapid Coat™ PVC is a tough, polyvinyl chloride based tape with special high tack adhesive formulated as the outer wrap for Wrapid Bond™ viscoelastic coated pipe. The high tack adhesive and tough backing provides an effective barrier to water and oxygen which provides effective corrosion protection and soil stress resistance.

#### **Chemical Resistance**

 Combined with Wrapid Bond, the system is resistant to corrosive salt water, soil acids, alkalies and salts, common chemicals, chemical vapors, and exposure to outdoor weathering and sunlight.

#### Flexibility & Adhesion

- Highly conformable, all-weather 0.50 mm (20 mil) thick tape designed for application over a wide temperature range.
- Very easy to apply at high or low temperatures it provides excellent adhesion and shear resistance.

#### **Long Term Corrosion Protection**

 In combination with Wrapid Bond<sup>™</sup>, the composition of both products is such that they provide an effective barrier to water and oxygen which enhances corrosion protection and soil stress resistance.





### **Applications**



Oil & Gas



Repair & Rehab



**Corrosion Coating** 



Girth-Weld Joints



Fittings & Bends



# Wrapid Coat™ PVC

### **Superior Mechanical Protection**

Typical Product Properties	Test Method	Typical Value
Color		Black
Thickness		0.50 mm (20 mils)
Elongation @ Break	ASTM D1000	200%
Tensile Strength	ASTM D1000	70.0 N/cm (40 pli)
Impact Strength	ASTM G14	15 J
Adhesion to Steel @ 12°C (54°F)	ASTM D1000	3.3 N/cm (1.9 pli)
Adhesion to Steel @ 23°C (74°F)	ASTM D1000	2.2 N/cm (1.3 pli)
Roll Unwind @ 12°C (54°F)	ASTM D1000	1.75 N/cm (1.0 pli)
Roll Unwind @ 23°C (74°F)	ASTM D1000	1.75 N/cm (1.0 pli)
Water Vapor Transmission Rate @ g/645 cm²/24 hrs.	ASTM D3833	1.0
Moisture Absorption	ASTM D570	.35%
Dielectric Strength	ASTM D1000	20 kv
Normal Application		-12°C to 65°C
Temperature Range		(+10°F to 150°F)
Normal Service		-48°C to 80°C
Temperature Range		(-55°F to 176°F)

<sup>\*</sup> This data is not to be used for specification. Values listed are for typical properties and should not be considered minimum or maximum.

Since 1967, Canusa-CPS has been a leading developer and manufacturer of specialty pipeline coatings for the sealing and corrosion protection of pipeline joints and other substrates. Canusa-CPS high performance products are manufactured to the highest quality standards and are available in a number of configurations to accommodate many specific project applications.

The product information shown here is intended as a guide for standard products.

Consult your Canusa representative for specific projects or unique applications.

#### Canusa-CPS A division of ShawCor Ltd.

#### **Head Office**

25 Bethridge Rd. Toronto, ON M9W 1M7 Canada

Tel: +1 416 743 7111 Fax: +1 416 743 5927

#### Canada

Suite 3200, 450 - 1st Street S.W. Calgary, AB T2P 5H1 Canada

Tel: +1 403 218 8207 Fax: +1 403 264 3649

#### **Americas**

2408 Timberloch Place, Building C-8 The Woodlands, TX 77380 USA

Tel: +1 281 367 8866 Fax: +1 281 367 4304

#### Europe, Middle East, Africa & Russia

Unit 3, Sterling Park,

Gatwick Road, Crawley, West Sussex RH10 9QT United Kingdom

Tel: +44 1293 541254 Fax: +44 1293 541777

#### Asia-Pacific

101 Thomson Road, #11-03 United Square 307591 Singapore

Tel: +65 6749 8918 Fax: +65 6749 8919

## Canusa-CPS is registered to ISO 9001:2008

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the product data sheet when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this data sheet is to be used as a guide and is subject to change without notice. This data sheet supersedes all previous data sheets on this product. E&OE

PDS\_Wrapid Coat PVC\_rev018



